

## Test Results

Property	Test Procedure	Result
VOCs	ASTM E595-06	0.011% by Weight
Water Absorption	ASTM D570	0.01% by Weight
Density	ASTM D792	133.0 lb/ft <sup>3</sup>
Specific Gravity	ASTM D792	2.13
Flexural Modulus	ASTM D790	8,617,000
Compressive Strength	ASTM D695	38,100
Flexural Strength	ASTM D790	13,600
Coefficient of Expansion and Contraction	ASTM D696	2.10 X 10 <sup>-5</sup>
Tensile Strength	ASTM D638	6,400
Rockwell Hardness	ASTM D785	113
Fire Resistance	ASTM D635	Self-Extinguishing
Heat Deflection	ASTM D648	325° F
Fungal Resistance	ASTM G 21	Pass
Bacterial Resistance	ASTM G 22	Pass
Nominal Thickness	1"	+/- .0625"
Nominal Weight	11 lbs. per sq.ft. (1" Thick)	N/A